



AIRCRAFT ALUMINUM FORMING TOLERANCE

Aircraft Extrusion Co
2700 Hegan Lane, STE168
Chico, CA 95928
www.aircraftextrusion.com

6.1.2.2.1 g (Continued)

TABLE I
MINIMUM STANDARDS
BEND RADII REQUIREMENTS FOR ALUMINUM ALLOY SHEET (Except 5456)*

Thickness in Inches	1100-0 2219-0 3003-0 5052-0 6061-0	2219-T42 2024-0 3003-H14 5052-H34 6061-T4			2219-T62 2219-T81 2024-T3 7075-0	7075-T6 7178-T6 6061-T6	
			2219-T31	7178-0	2024-T4 2219-T87	7178-T6 2024-T36	2024-T85
0.016	0.03	0.03	0.03	0.03	0.06	0.09	0.25
0.020	0.03	0.03	0.06	0.03	0.06	0.09	0.25
0.025	0.03	0.06	0.06	0.06	0.09	0.12	0.31
0.032	0.03	0.06	0.06	0.06	0.12	0.16	0.44
0.036	0.03	0.06	0.09	0.06	0.16	0.19	0.50
0.040	0.06	0.06	0.09	0.06	0.16	0.19	0.56
0.045	0.06	0.09	0.09	0.09	0.19	0.25	0.62
0.050	0.06	0.09	0.12	0.09	0.19	0.25	0.62
0.056	0.06	0.12	0.12	0.12	0.22	0.28	0.62
0.063	0.06	0.12	0.16	0.12	0.22	0.31	0.75
0.071	0.09	0.12	0.16	0.12	0.28	0.38	0.88
0.080	0.09	0.16	0.19	0.19	0.34	0.44	1.12
0.090	0.09	0.19	0.19	0.19	0.38	0.50	1.25
0.100	0.12	0.22	0.25	0.22	0.44	0.62	1.75
0.112	0.12	0.25	0.34	0.28	0.50	0.75	
0.125	0.12	0.25	0.50	0.28	0.56	0.88	
0.140	0.12	0.34	0.56	0.38	0.62	1.00	
0.160	0.16	0.38	0.62	0.44	0.75	1.12	
0.180	0.19	0.44	0.69	0.50	0.88	1.25	
0.190	0.28	0.50	0.75	0.56	0.88	1.25	

+/- 0.01 for 0.03 to 0.06

+/- 0.03 for 0.09 and larger

TABLE II
MINIMUM STANDARD
BEND RADII REQUIREMENTS FOR 5456 ALUMINUM ALLOY
SHEET

Thickness Inches	Temper			
	-0	-H321	-H323	-H343
0.03	0.06	0.09	0.12	0.19
0.06	0.09	0.19	0.25	0.31
0.09	0.12	0.25	0.37	0.44
0.12	0.19	0.37	0.50	0.62
0.18	0.31	0.50	0.75	0.88
0.25	0.50	0.75	1.12	1.37
0.37	0.75	1.50	---	---
0.50	1.00	2.00	---	---

+/- 0.01 for 0.03 to 0.06

+/- 0.03 for 0.09 and larger